



TYPE **Ripo™ RC**
Ripo™ WB
Ripo™ PS

TECHNICAL DATA FOR RIPO

Item	Ripcord construction	Nb of roving	Breaking strength (N)	Elongation at break (%)	Cord weight (g/1000 m)	Diameter approx. (mm)
1	1680 dtex x 1Z90	1	≥ 300	2,0 – 4,4	160 – 190	0,4
2	3360 dtex x 1Z75	2	≥ 575	2,0 – 4,4	320 – 375	0,6
3	1680 dtex x 1 Z240 x 3 S160	3	≥ 800	2,8 – 5,5	500 – 570	0,8
4	1680 dtex x 1 Z150 x 3 S100	3	≥ 880	2,8 – 5,5	480 – 550	0,8

Ripo™ RC is standard Aramid ripcord.

Ripo™ WB is waterblocking Aramid ripcord.

Ripo™ PS is a non-wicking colored Aramid ripcord.

Mechanical properties are determined in accordance with the Aramid Standard Test Methods.

STANDARD MAKE-UP FOR RIPO

Tube	mm	290 x 94
Yarn weight per bobbin item 1,2 & 4	kg	approx. 4,5
Yarn weight per bobbin item 3	kg	approx. 9,5
Bobbin outer diameter, approx.	mm	180 or 245
Package sizes	bobbins per box	90 (4,5 kg) 39 (9,5 kg)